

Keep up with us on



FOUNDER'S RESERVE 73

100% Acrylic Exterior Finish System



Available in:

210 Series Flat

212 Series Satin



WINTER



SPRING



SUMMER



AUTUMN

FOUNDER'S RESERVE 73

100% Acrylic Exterior Finish System



Founder's Reserve 73

FLAT EXTERIOR FINISH

210 Series: Founder's Reserve Exterior Flat is a premium 100% acrylic exterior flat finish which provides lasting service over new or previously painted surfaces in good condition. The product has excellent color retention, superior adhesion and a tight film that resists dirt pick-up. Founder's Reserve will provide a durable and protective finish on any properly prepared exterior surface. Recommended for use on vertical aluminum, vinyl, wood, engineered wood and fiber cement siding; masonry and primed metal surfaces down to surface and air temperature of 35°F. Founder's Reserve has very good early moisture resistance which all but eliminates surfactant leaching.

Property	Result
Volume Solids	36.7 %
Viscosity	95 - 100 (Krebs units)
Density	10.88 lbs./gal
VOC	< 100 g/L
Gloss @ 85°	3 - 8
Spread Rate	350 - 400 sq. ft./gal
Recommended Film Thickness	4.0 - 4.6 mils wet 1.47 - 1.69 mils dry
Dry to touch	1 hour
Recoat	4 hours
Reducer	Water



FOUNDER'S RESERVE 73

SATIN EXTERIOR FINISH

212 Series: Founder's Reserve Exterior Satin is a premium 100% acrylic exterior satin finish which provides lasting service over new or previously painted surfaces in good condition. The product has excellent color retention, superior adhesion and a soft satin sheen that resists dirt pick-up. Founder's Reserve will provide a durable and protective finish on any properly prepared exterior surface. Recommended for use on vertical aluminum, vinyl, wood, engineered wood and fiber cement siding; masonry and primed metal surfaces down to surface and air temperature of 35°F. Founder's Reserve has very good early moisture resistance which all but eliminates surfactant leaching.

Property	Result
Volume Solids	36.9 %
Viscosity	95 - 100 (Krebs units)
Density	10.37 lbs./gal
VOC	< 130 g/L
Gloss @ 60°	16 - 20
Spread Rate	350 - 400 sq. ft./gal
Recommended Film Thickness	4.0 - 4.6 mils wet 1.47 - 1.69 mils dry
Dry to touch	1 hour
Recoat	4 hours
Reducer	Water